Dielectric and pyroelectric properties of sintered discs of sodium meta vanadate

A H KHAN, D B GHARE* and P S NARAYANAN**

Department of Physics, Jahangirnagar University, Savar, Dacca, Bangladesh

* Department of High Voltage Engineering,

** Department of Physics, Indian Institute of Science, Bangalore 560 012, India

MS received 2 July 1982; revised 16 August 1982

Abstract. The dielectric and pyroelectric properties of poled and unpoled sintered discs of sodium meta vanadate were investigated in the temperature range from room temperature to 450°C. Dielectric constant and loss tangent anomalies were found around 375–390°C, while in pyroelectric coefficient, two anomalies were noticed at $250 \pm 25^\circ\text{C}$ and $360 \pm 50^\circ\text{C}$ respectively.

Keywords. Ferroelectricity; pyroelectric behaviour; phase transition; sodium meta vanadate; sintered dielectric materials.

1. Introduction

Sawada and Nomura (1951) reported that NaVO_3 is ferroelectric below 380°C. Matsuda (1974) studied the dielectric dispersion in NaVO_3 single crystals grown by Czochralski technique. Shaikh *et al* (1978) and Ramani *et al* (1975) described the structural features of NaVO_3 single crystals and the variations in lattice parameters in the temperature range from room temperature to 500°C. The growth of NaVO_3 and a detailed laser Raman and infrared study were undertaken to find out the exact structural features at room temperature and the origin of ferroelectricity in NaVO_3 . Sintered ceramic discs of NaVO_3 were prepared to study its pyroelectric behaviour and ϵ_r , and it was found that the ceramic discs showed an unusually large ϵ_r near the transition temperature.

2. Experimental procedure

Polycrystalline sodium metavanadate powder (10 – 50 μm) (LR 99.8%) was pressed in the form of discs (18 mm diam; thickness 0.5–2 mm) at a pressure of 300 kg/cm². The discs were sintered in a platinum crucible at 520°C for 3 hr and then allowed to cool to room temperature inside the furnace after it was switched off. The samples were polished and three different types of electrodes used for making electrical contacts (on different samples), with air-drying silver paste and vacuum-evaporated aluminium and chromium films.

The capacitance and $\tan \delta$ *vs* temperature were measured in the temperature range from room temperature to 450°C using Marconi Universal Bridge No. TF 1313 at 1 and 10 kHz. Pyroelectricity was measured in the same temperature range by uniformly heating the sample at 1.2°C per min using the Keithley digital microvoltmeter (model No. 177) and the pyroelectric coefficients were calculated using equations given by Lang *et al* (1965a). Poling of the samples was carried out at 220°C for 15 min at a field strength of 3 kV/cm. The dielectric constant ϵ_r , $\tan \delta$, and pyroelectric coefficient *vs* temperature measurements were repeated on pol-ed samples, in the same temperature range, to determine the effect of such poling operation on these properties of the material.

3. Results and discussion

The graphs of dielectric loss ($\tan \delta$) as a function of temperature measured at 1 and 10 kHz given in the inset of figure 1 show that the loss tangent at 1 kHz increased beyond the compensation range provided in the bridge at temperatures above 200°C. Further measurements of ϵ_r upto 450°C were therefore carried out at 10 kHz only.

Figure 1. Variations in relative permittivity as a function of temperature for sintered discs of NaVO_3 . **A,B.** Aluminium electrode, before and after poling respectively at 10 kHz. **C,D.** Chromium electrode before and after poling respectively at 10 kHz. (Inset) Variations in $\tan \delta$ as a function of temperature. **A,B,C** and **D** as above. **E,F.** Silver electrode before and after poling respectively at 1 kHz.

The maxima in $\tan \delta$ at 10 kHz shift to a higher temperature which is in agreement with the results reported by Matsuda (1974) on NaVO_3 single crystals. The dielectric constant of the sintered disc samples (at 10 kHz) (figure 1) increased sharply above 200°C , exhibited a small dip at around 380°C and continued to increase further. Similar behaviour was noticed at corresponding temperatures in the graphs of $\tan \delta$ *vs* temperature (at 10 kHz). It can also be seen that the dip in ϵ_r around 380 – 390°C is independent of electrode material and poling. After poling the rate of increase in ϵ_r as a function of temperature, in the temperature range 200 – 350°C is much sharper and a linear relationship exists between $\log \epsilon_r$ and temperature. For poled samples the relationship between $\log (\tan \delta)$ *vs* temperature is also almost linear in the temperature range between 200 and 300°C .

One finds that the relative permittivity increases exponentially at temperatures above 400°C which is unexpected if a ferroelectric-paraelectric transition has taken place at 380 – 390°C . The differential thermal analysis (DTA) and differential scanning calorimetric (DSC) studies on sodium meta vanadate powders in the temperature range from room temperature to 500°C also did not reveal any signs of a first order transition around $380^\circ\text{C} \pm 20^\circ\text{C}$. Thus this dielectric behaviour may be explained on the basis of slight nonstoichiometric conditions created at high temperatures by the loss of oxygen (similar to the behaviour reported on vanadium bronzes by Pletneva *et al* 1979; Volkov *et al* 1976).

The plots of pyroelectric coefficient as a function of temperature are shown in figure 2. Samples with silver paste electrodes initially exhibited several anomalous peaks and dips in the first run only (not shown in figure 2). In subsequent repetitions of these measurements only two peaks are however observed corresponding to temperatures around 240 and 340°C respectively. The other peaks exhibited by all samples at the same corresponding temperatures in their first run of measurements were identified due to the effect of this kind, depending on electrode

Figure 2. Variations in pyroelectric coefficient as a function of temperature for sintered discs of NaVO_3 . A, B. Silver electrode before and after poling respectively. C, D. Aluminium electrode before and after poling respectively. E, F. Chromium electrode before and after poling respectively.

Table 1. Data on position of peaks in the pyroelectric coefficient exhibited by NaVO_3 sintered discs.

Electrode material	Position of peak No. 1 w.r.t. temperature ($^{\circ}\text{C}$)		Position of peak No. 2 w.r.t. temperature ($^{\circ}\text{C}$)	
	Unpoled sample	Poled sample	Unpoled sample	Poled sample
Silver paste	255	240	330	340
Aluminium (vacuum evaporated)	280	275	400	390
Chromium (vacuum evaporated)	260	275	420	380

material during its first firing operations. This was also confirmed by the fact that the samples with aluminium and chromium vacuum evaporated electrodes did not exhibit these additional peaks and dips even in their first run of measurements.

The plots of pyroelectric coefficient as a function of temperature shown in figure 2 are the stabilised values obtained in subsequent runs. The pyroelectric coefficient exhibited by samples with aluminium and chromium vacuum evaporated electrodes also shows two peaks at temperatures as summarised in table 1.

It can be seen from table 1 that the position of these two peaks (with respect to temperature) were slightly altered as a result of change in the electrode material. The poling did not lead to any substantial change in the position of the peaks, even though it resulted in increase of the magnitude of the pyroelectric coefficient by almost one order of magnitude in all types of samples. It is therefore definite that NaVO_3 belongs to the polar class at room temperature and above 380°C it is nonpolar.

4. Conclusions

The dielectric constant *vs* temperature characteristics of sintered discs of NaVO_3 exhibited steeply rising values of ϵ_r in the temperature range 200 to 450°C . In view of the very high ohmic values of the samples at high temperatures and high field strengths, this phenomenon seems to be intrinsic in nature and cannot be attributed only to grain boundary effects. The DTA and DSC data did not show any evidence of a first order transition at 380°C . The pyroelectric coefficient variation with temperature has been used to establish that NaVO_3 belongs to the polar class at room temperature and that its high temperature phase is non-polar.

Acknowledgements

The authors wish to thank Prof. R Srinivasan, and Prof. V Prabhaskar, (Indian Institute of Science) for their assistance. Thanks are due to Mr Seetharam for placing

at their disposal some of his thermal and optical results under publication. One of the authors (AHK) also wishes to thank the authorities of the Jahangirnagar University and UGC.

References

- Lang S B and Steal F 1965a *Rev. Sci. Instrum.* **36** 929
Lang S B and Steal F 1965b *Rev. Sci. Instrum.* **36** 1817
Matsuda M 1974 *J. Phys. Soc. Jpn.* **36** 759
Pletneva E D, Khodos M Ya, Volkov V L and Fotiev A A 1979 *Inorganic materials (USA)* **15** 670
Ramani K, Shaikh A M, Reddy B S and Viswamitra M A 1975 *Ferroelectrics* **9** 49
Sawada S and Nomura S 1951 *J. Phys. Soc. Jpn.* **6** 192
Shaikh A M, Viswamitra M A and Narayanan P S 1978 *Ferroelectrics* **20** 311
Volkov V L, Kapustkin V K, Fotiev A A and Miroshnikova L D 1976 *Inorganic Materials (USA)* **12** 1795