

Estimation of CE–CVM energy parameters from miscibility gap data

G SRINIVASA GUPTA, G VAMSI MADHAV, A PANDEY, B NAGESWARA SARMA*
and S LELE

Centre of Advanced Study, Department of Metallurgical Engineering, Institute of Technology, Banaras Hindu University, Varanasi 221 005, India

MS received 10 May 2004

Abstract. The powerful framework of cluster expansion–cluster variation methods (CE–CVM) expresses alloy free energy in terms of energy (model) parameters, macroscopic variables (composition and temperature) and microscopic variables (correlation functions). A simultaneous optimization of thermodynamic and phase equilibria data using CE–CVM is critically dependent on giving good initial values of energy parameters, macroscopic and microscopic variables, respectively. No standard method for obtaining the initial values of the energy parameters is available in literature. As a starting point, a method has been devised to estimate the values of energy parameters from consolute point (miscibility gap maximum) data. Empirical relations among energy parameters, temperature (T_c), composition (x_c) and d^2T/dx^2 at the consolute point, have been developed using CE–CVM free energy functions for *bcc* and *fcc* structures in the tetrahedron and tetrahedron–octahedron approximations, respectively. Thus from the observed data of T_c , x_c and d^2T/dx^2 in the above relations, good initial values of energy parameters can be obtained. Further, a necessary modification to the classical NR method for solving simultaneous nonlinear/transcendental equations with a double root in one variable and a simple root in the other has been presented.

Keywords. Cluster expansion method; cluster variation method; *bcc* and *fcc* structures; consolute point; miscibility gap; Newton–Raphson method.

1. Introduction

The framework of cluster expansion (CE) method due to Sanchez *et al* (1984) and cluster variation method (CVM) proposed by Kikuchi (1951) offers a physically meaningful and mathematically tractable hierarchy of approximations to handle the ever-present short range order in materials systems. It also subsumes many of the classical approximations of the alloy problem as lower levels of the hierarchy. In fact, CE–CVM has become the method of choice for computation of phase diagrams and thermodynamics of materials systems using the energy parameters estimated from first-principles quantum mechanical calculations (de Fontaine 1994). While the first-principles calculations have been quite successful in obtaining the correct topologies of the phase diagrams, the quantitative agreement with the observed data needs significant improvement (Saunders and Miodownik 1998). In view of this, it becomes important to be able to find an optimized set of model parameters for the case of standard CE–CVM approximations in different materials systems. These parameters will characterize the chosen alloy system if they are found by simultaneous (nonlinear) optimization of all types of available thermodynamic and phase equi-

libria data. Success of these nonlinear optimization procedures critically depends on the ability to provide good initial values for the model parameters. If appropriate initial values are not chosen, the topology of the phase diagram will be different from that of the observed one. Under such circumstances, the errors (the deviations between the calculated and observed compositions/temperatures) cannot even be evaluated, leading to a breakdown of the optimization procedure. Even so, there is no standard procedure for estimating the initial values of CE–CVM model parameters available in literature. In this communication, we present the details of an empirical procedure using which the model parameters can be estimated from the miscibility gap data in binary systems. In § 2, a brief outline of the CE–CVM formulations of free energy for disordered binary *bcc* and *fcc* structures is presented. A modified Newton–Raphson method for the determination of consolute point (miscibility gap maximum) is presented in § 3, whereas an empirical procedure for the estimation of CE–CVM energy parameters from miscibility gap data is given in § 4.

2. CE–CVM formulations for *bcc* and *fcc* structures

For the sake of completeness, a brief outline of the CE–CVM formulations for disordered binary *bcc* (Ackerman

*Author for correspondence (drbnsarma@yahoo.com)

et al 1989) and *fcc* (Sanchez and de Fontaine 1978) structures, respectively under tetrahedron and tetrahedron–octahedron approximations is given below. An excellent review on this subject by Inden and Pitsch (1991) may be consulted for the details of cluster algebra. As usual, we shall present the results for a typical choice of energy parameters in an orthogonal basis corresponding to the following relations among the site operator, \mathbf{s}_i , and the site occupation operators p_i^A and p_i^B :

$$\begin{bmatrix} 1 \\ \mathbf{s}_i \end{bmatrix} = \begin{bmatrix} 1 & 1 \\ -1 & 1 \end{bmatrix} \begin{bmatrix} p_i^A \\ p_i^B \end{bmatrix}. \quad (1)$$

The four vertices of the tetrahedron motif in *bcc* are labelled 1, 2, 3 and 4, respectively such that 12, 23, 34 and 14 distances represent first neighbour pairs while 13 and 24 represent second neighbour pairs. All the triangles forming part of the motif are crystallographically identical. Accordingly we have the following correlation functions (u_i): $\langle \mathbf{s}_1 \mathbf{s}_2 \rangle$, $\langle \mathbf{s}_1 \mathbf{s}_3 \rangle$, $\langle \mathbf{s}_1 \mathbf{s}_2 \mathbf{s}_3 \rangle$, $\langle \mathbf{s}_1 \mathbf{s}_2 \mathbf{s}_3 \mathbf{s}_4 \rangle$ and $\langle \mathbf{s}_1 \rangle$. Of these, the point correlation function $\langle \mathbf{s}_1 \rangle$ is related to composition through the relation $\langle \mathbf{s}_1 \rangle = -x_A + x_B = 2x_B - 1$ and is fixed for an alloy of fixed composition. Thus, we have 4 independent correlation functions which describe the microscopic state of the system. The probabilities of occurrence of different types of atomic arrangements on the motif/submotif sites are called cluster variables. There are a total of 20 distinct clusters present in the structure. These cluster probabilities are linear functions of u_i .

Following the CE method, the configurational energy of the system is expressed as a bilinear sum of the products of the u_i (along with the appropriate multiplicities of the submotifs) and the corresponding energy coefficients, e_i . The configurational entropy can be obtained by using CVM through appropriate linear combinations of the Boltzmann entropy summations of cluster probabilities corresponding to each of the motif/submotifs, such that each of the cluster/subcluster configurations is counted only once. This is done through the so-called Kikuchi–Barker overlap correction coefficients (Kikuchi 1951; Barker 1953).

Thus the free energy of the system is expressed as a function of the model energy parameters (e_i), the macroscopic variables (composition, x_B and temperature, T) and the microscopic internal variables (u_i) in a hierarchical manner. Similar formulation has been carried out for disordered binary *fcc* structure using regular tetrahedron and octahedron as motifs (Sanchez and de Fontaine 1978). In this case, there are a total of 9 correlation functions (and hence 9 energy parameters) apart from the point correlation function. These correspond to first neighbour pair, second neighbour pair, basal (equilateral) triangle, lateral (isosceles) triangle, regular tetrahedron, irregular tetrahedron, square, 5-point pyramid and octahedron. The free energy expression is obtained as in the case of *bcc*.

3. Determination of consolute point

The composition, x_c and temperature, T_c , of the consolute point can be determined from the following set of two equations (Lupis 1983):

$$\frac{\partial^2 G}{\partial x^2} = 0, \quad (2)$$

and

$$\frac{\partial^3 G}{\partial x^3} = 0, \quad (3)$$

where G is a function of x and T . Introducing standard notation for partial derivatives, these equations can be written as

$$G_{xx} = 0, \quad (2a)$$

and

$$G_{xxx} = 0. \quad (3a)$$

Explicit solutions for x_c and T_c as given, for example, by Lupis (1983) cannot be found in the present case, because the internal variables u_i have an implicit variation with x and T . Hence, they have to be determined for each x and T by minimizing G . Thus, x_c and T_c can be found by using numerical procedures such as the Newton–Raphson (NR) method by a simultaneous solution of equations in (2) and (3). Since the second and third partial derivatives of G have to be simultaneously zero at the consolute point, we have a double root in x but a simple root in T (Mathews 1998). The NR procedure needs to be modified for such cases, as given below.

Consider a function, $f(x, T)$, which has a double root at x_0 in x and a simple root at T_0 in T . Further, consider a Taylor expansion of $f(x, T)$ and $f_x(x, T)$ around x and T .

$$\begin{aligned} f(x_0, T_0) &= f(x, T) + (x_0 - x)f_x(x, T) + \frac{1}{2}(x_0 - x)^2 \\ & f_{xx}(x, T) + (x_0 - x)(T_0 - T)f_{xT}(x, T) + (T_0 - T)f_T(x, T), \end{aligned} \quad (4)$$

$$f_x(x_0, T_0) = f_x(x, T) + (x_0 - x)f_{xx}(x, T) + (T_0 - T)f_{xT}(x, T). \quad (5)$$

Note that only the first order deviations in x and T are considered in (5). All the derivatives present in (5) and lower ones are retained in (4). Solving (5) for $(T_0 - T)$ after setting the left hand side to zero, we have

$$(T_0 - T) = -\frac{f_x + (x_0 - x)f_{xx}}{f_{xT}}. \quad (6)$$

Substituting (6) in (4) and simplifying, we obtain

$$f_{xx}f_{xT}(x_0 - x)^2 + 2f_{xx}f_T(x_0 - x) - 2(ff_{xT} - f_x f_T) = 0. \quad (7)$$

This is a quadratic in $(x_0 - x)$ and can be easily solved to yield the Newton step for x .

$$(x_0 - x) = \frac{-f_{xx}f_T \pm \sqrt{(f_{xx}f_T)^2 + 2f_{xx}f_{xT}(ff_{xT} - f_x f_T)}}{f_{xx}f_{xT}}. \quad (8)$$

For positive (negative) values of $f_{xx}f_T$, the positive (negative) sign should be selected for the discriminant. Substituting (8) in (6) then yields an expression for $(T_0 - T)$. For very small departures from the correct solution, $f_{xx}f_T$ can be taken out as a common factor from the discriminant in (8), the remainder can be expanded using binomial theorem and retaining only the leading term in the same to obtain

$$(x_0 - x) = (ff_{xT} - f_x f_T) / (f_{xx} f_T). \quad (9)$$

Note that the above method can be utilized to find the consolute point in which $f(x, T) = G_{xx}$ and $f_x(x, T) = G_{xxx}$. The NR iterations are carried out using these corrections till a suitable convergence criterion (e.g. the magnitudes of G_{xx} and G_{xxx} are less than, say, 0.001) is met.

4. Estimation of energy parameters from miscibility gap data

Consolute point data consist of the critical temperature, T_c , composition, x_c and the curvature of the miscibility gap boundary at the consolute point, which is related to $(d^2T/dx^2)_{(T_c, x_c)} = T_{xx}$. This T_{xx} is in fact equal to $(1/3)[(\partial^4 G/\partial x^4)/(\partial^2 S/\partial x^2)]$ [see Lupis (1983) for details]. These quantities have been obtained for *bcc* disordered structure in the tetrahedron approximation by using the modified Newton–Raphson method presented in the previous section for an initial choice of energy parameters, $e_1 = -250 \text{ J mol}^{-1}$, $e_2 = 2e_1/3$ and $e_3 = e_4 = 0$. These are $T_c = 305.825 \text{ K}$, $x_c = 0.5$ and $T_{xx} = -397.209 \text{ K}$. This choice of $e_2 = 2e_1/3$ makes the total contribution of first and second neighbour pairs to the enthalpy of *bcc* structure comparable to that from first neighbours in *fcc* structure. By varying the ratios, e_3/e_1 and e_4/e_1 , in the range from 0.2 to -0.2 in steps of 0.1, the consolute point data mentioned above have been obtained and given in table 1.

By fitting suitable polynomial functions of e_3/e_1 and e_4/e_1 to the tabulated data for T_c , x_c and T_{xx} , the following relations have been obtained.

$$x_c^{\text{obs}} = 0.5 + 0.394714(e_3/e_1)^{3/5} + 0.536611(e_3/e_1)^{3/5}(e_4/e_1), \quad (10)$$

$$T_c^{\text{obs}} = e_1[-1.2233 - 5.25314(e_3/e_1)^2 - 0.763127(e_4/e_1) - 4.46246(e_3/e_1)^2(e_4/e_1)], \quad (11)$$

$$T_{xx}^{\text{obs}} = e_1[1.58884 + 30.9369(e_3/e_1)^2 - 1.73767(e_4/e_1) + 83.8545(e_3/e_1)^2(e_4/e_1)]. \quad (12)$$

Division of (11) with (12) eliminates the individual e_1 term and gives the following equation in e_3/e_1 and e_4/e_1 .

$$(5.25314T_{xx}^{\text{obs}} + 30.9369T_c^{\text{obs}})(e_3/e_1)^2 + (0.763127T_{xx}^{\text{obs}} - 1.73767T_c^{\text{obs}})(e_4/e_1) + (4.46246T_{xx}^{\text{obs}} + 83.8545T_c^{\text{obs}})(e_3/e_1)^2(e_4/e_1) + 1.2233T_{xx}^{\text{obs}} + 1.58884T_c^{\text{obs}} = 0. \quad (13)$$

By substituting $e_4/e_1 = 0$ in (10) and solving for e_3/e_1 , we get an approximate value for e_3/e_1 . These can be used as initial values for simultaneously solving (10) and (13) for e_3/e_1 and e_4/e_1 using two-dimensional Newton–Raphson method. Substitution of these in (11) or (12) gives e_1 , from which e_3 and e_4 can be found.

The energy parameters thus found can be used for obtaining the corresponding consolute point data for comparison with the observed data in order to test the validity of this procedure. Results of a couple of such tests are summarized in table 2. Comparison of observed and calculated data reveals that the differences in calculated and observed data are well within tolerable limits and the topology of the phase diagram can be reproduced very

Table 1. Consolute point data for disordered *bcc* structure in the tetrahedron approximation.

e_3/e_1	e_4/e_1	T_c (K)	x_c	T_{xx} (K)
0.2	0.2	406.179	0.685289	-799.585
0.2	0.1	380.245	0.668601	-725.385
0.2	0.0	355.789	0.650946	-675.977
0.2	-0.1	333.092	0.633034	-650.112
0.2	-0.2	312.543	0.615662	-646.647
0.1	0.2	364.967	0.63705	-494.972
0.1	0.1	341.936	0.615201	-478.627
0.1	0.0	320.37	0.595764	-485.075
0.1	-0.1	300.497	0.579158	-508.214
0.1	-0.2	282.755	0.565332	-546.61
0.0	0.2	345.203	0.5	-279.681
0.0	0.1	325.147	0.5	-341.866
0.0	0.0	305.825	0.5	-397.209
0.0	-0.1	287.715	0.5	-451.324
0.0	-0.2	271.472	0.5	-511.098
-0.1	0.2	364.967	0.36295	-494.972
-0.1	0.1	341.936	0.384799	-478.627
-0.1	0.0	320.370	0.404236	-485.075
-0.1	-0.1	300.497	0.420842	-508.214
-0.1	-0.2	282.755	0.434668	-546.61
-0.2	0.2	406.179	0.314711	-799.585
-0.2	0.1	380.245	0.331399	-725.385
-0.2	0.0	355.789	0.349054	-675.977
-0.2	-0.1	333.092	0.366966	-650.112
-0.2	-0.2	312.543	0.384338	-646.647

Table 2. Comparison of observed and calculated data for *bcc* structure.

Initial choice of energies (J mol ⁻¹)	Consolute point data for the initial choice of energies	Energies calculated from (10)–(13) (J mol ⁻¹)	Consolute point data for the calculated energies
$e_1 = -250$ $e_2 = -500/3$ $e_3 = 50$ $e_4 = 50$	$T_c = 312.543$ K $x_c = 0.38433$ $T_{xx} = -646.64$ K	$e_1 = -245.998$ $e_2 = -163.999$ $e_3 = 49.6889$ $e_4 = 43.4941$	$T_c = 312.747$ K $x_c = 0.379574$ $T_{xx} = -637.831$ K
$e_1 = -250$ $e_2 = -500/3$ $e_3 = 50$ $e_4 = 0$	$T_c = 355.89$ K $x_c = 0.349054$ $T_{xx} = -675.57$ K	$e_1 = -247.511$ $e_2 = -165.007$ $e_3 = 46.805$ $e_4 = -7.05899$	$T_c = 354.463$ K $x_c = 0.348275$ $T_{xx} = -656.571$ K

Table 3. Consolute point data for disordered *fcc* structure.

e_3/e_1	e_5/e_1	T_c (K)	x_c	T_{xx} (K)
0.2	0.2	327.975	0.634889	-433.94
0.2	0.1	325.959	0.625987	-458.815
0.2	0.0	324.083	0.617829	-489.58
0.2	-0.1	322.339	0.610353	-526.321
0.2	-0.2	320.729	0.603475	-569.23
0.1	0.2	310.185	0.580431	-325.856
0.1	0.1	308.656	0.573463	-359.551
0.1	0.0	307.17	0.567457	-398.323
0.1	-0.1	305.725	0.562235	-442.574
0.1	-0.2	304.333	0.557636	-492.867
0.0	0.2	303.447	0.5	-280.81
0.0	0.1	302.185	0.5	-319.389
0.0	0.0	300.903	0.5	-362.215
0.0	-0.1	299.611	0.5	-410.004
0.0	-0.2	298.326	0.5	-463.596
-0.1	0.2	310.185	0.419569	-325.856
-0.1	0.1	308.656	0.426537	-359.551
-0.1	0.0	307.170	0.432543	-398.323
-0.1	-0.1	305.725	0.437765	-442.574
-0.1	-0.2	304.333	0.442364	-492.867
-0.2	0.2	327.975	0.365111	-433.94
-0.2	0.1	325.959	0.374013	-458.815
-0.2	0.0	324.083	0.382171	-489.58
-0.2	-0.1	322.339	0.389647	-526.321
-0.2	-0.2	320.729	0.396525	-569.23

well. Hence the estimated energies can serve as very good starting values for CE–CVM optimization programs.

As in the case of *bcc* disordered structure, consolute point data have been obtained for *fcc* disordered structure in the tetrahedron–octahedron approximation by using modified Newton–Raphson method for an initial choice of $e_1 = -250$ J mol⁻¹ and $e_j = 0$ ($j = 2$ to 9). These are $T_c = 300.903$ K, $x_c = 0.5$ and $T_{xx} = -362.215$ K. In general, the energies corresponding to all the submotifs containing second neighbour distances have been neglected in the literature. Accordingly, we set $e_2 = e_4 = e_6 = e_7 = e_8 = e_9 = 0$ and vary the ratios, e_3/e_1 and e_5/e_1 , in the range from -0.2 to 0.2 in steps of 0.1 , and obtain the corresponding consolute point data which are given in table 3.

Once again by fitting suitable polynomial functions of e_3/e_1 and e_5/e_1 to the tabulated data for T_c , x_c and T_{xx} , the following relations have been obtained for *fcc* structure.

$$x_c^{\text{obs}} = 0.5 + 0.299259(e_3/e_1)^{3/5} + 0.212183(e_3/e_1)^{3/5}(e_5/e_1), \quad (14)$$

$$T_c^{\text{obs}} = e_1[-1.20361 - 2.34275(e_3/e_1)^2 - 0.0526217(e_5/e_1) - 0.501314(e_3/e_1)^2(e_5/e_1)], \quad (15)$$

$$T_{xx}^{\text{obs}} = e_1[1.44886 + 13.531(e_3/e_1)^2 - 1.79837(e_5/e_1) + 11.2606(e_3/e_1)^2(e_5/e_1)]. \quad (16)$$

Once again, this set of equations can be solved in a manner similar to that of the *bcc* case. Further, this procedure has been verified to be valid and the differences among observed and estimated data have been well within the permissible limits.

The empirical fits given above span the range -0.2 to $+0.2$ for the energy parameter ratios and cover an asymmetry of the x_c which is commonly observed in real systems. While the relations found here may be valid for small extrapolations outside the domain considered, this procedure can be extended by considering wider ranges of energy parameter ratios to cover greater degree of asymmetry of the x_c , depending on a specific requirement. It may be noted that the solution of the (empirical) polynomial equations given above involves NR iterations in itself. Hence care should be exercised to obtain real and meaningful solutions for the energy parameter ratios.

It may be pointed out that the modified NR (presented in § 3) for the case of a double root in x and a simple root in T is applicable to the determination of two other special points in phase diagrams: (i) critical point of an order–disorder boundary (first order transition)—This is given by $\Delta G(x, T) = G^a - G^b = 0$ and $\Delta G_x(x, T) = G_x^a - G_x^b = 0$, where one of the phases is ordered, the other being disordered and (ii) congruent extrema in two phase boundaries. This case is very similar to that of the critical point in (i) except that the two phases involved need not be structurally related to each other.

5. Conclusions

A method has been devised to establish empirical relations among CE–CVM energy parameters and the observed consolute point data from phase diagrams. Using these relations, good initial estimates of parameters can be obtained. These parameters reproduce the observed topology of the phase diagrams and can thus be used for subsequent simultaneous optimization of thermodynamic, structural and phase equilibria data for materials systems. Further, a necessary modification to the classical NR method for solving simultaneous nonlinear/transcendental equations with a double root in one variable and a simple root in the other has been presented. Three applications of the modified NR method to find special points in phase diagrams have also been pointed out.

Acknowledgements

This investigation forms part of the Ph.D. research of the first author. He is grateful to the Principal and the management of the VNR Vignanjyothi Institute of Engineering and Technology, Kukatpally, Hyderabad, for giving him study leave for pursuing Ph.D. research at the Banaras

Hindu University, Varanasi. He is also grateful to the Head, Department of Metallurgical Engineering, for providing facilities. Financial support through a senior research fellowship from the Institute of Technology is also acknowledged.

References

- Ackermann H, Inden G and Kikuchi R 1989 *Acta Metall.* **37** 1
Barker J A 1953 *Proc. R. Soc.* **A216** 45
de Fontaine D 1994 *Solid State Phys.* **47** 33
Inden G and Pitsch W 1991 in *Materials science and technology* (ed.) P Haasen (Weinheim: VCH, Verlagsgesellschaft) Vol. **5**, pp. 497–552
Kikuchi R 1951 *Phys. Rev.* **81** 988
Lupis C H P 1983 *Chemical thermodynamics of materials* (Amsterdam: North Holland) pp. 225–226
Mathews J H 1998 *Numerical methods for mathematics, science and engineering* (New Delhi: Prentice-Hall) 2nd ed.
Sanchez J M and de Fontaine D 1978 *Phys. Rev.* **B17** 2926
Sanchez J M, Ducastelle F and Gratias D 1984 *Physica* **A128** 334
Saunders N and Miodownik A P 1998 *CALPHAD (Calculation of phase diagrams): A comprehensive guide* (Oxford: Pergamon)