Synthesis of CaTiO_3 from calcium titanyl oxalate hexahydrate (CTO) as precursor employing microwave heating technique

B M PATIL, R S SRINIVASA[†] and S R DHARWADKAR*

Department of Chemistry, The Institute of Science, 15, Madam Cama Road, Mumbai 400 032, India

[†]Department of Metallurgical Engineering & Materials Science, Indian Institute of Technology, Mumbai 400 076, India

MS received 30 June 2006; revised 16 April 2007

Abstract. Calcium titanate, CaTiO_3 , an important microwave dielectric material and one of major phases in synroc (synthetic rock), a titanate ceramic with potential application for fixation of high level nuclear waste was synthesized from calcium titanyl oxalate [$\text{CaTiO}(\text{C}_2\text{O}_4)_2 \cdot 6\text{H}_2\text{O}$] (CTO) by employing microwave heating technique. CTO heated in microwave heating system in air at 500°C for 1 h gave a perovskite, CaTiO_3 . The product obtained by heating of CTO in the same system at 700°C for the same duration was however, much more crystalline. CaTiO_3 obtained by the present method was characterized by X-ray diffraction (XRD), scanning electron microscopy (SEM) and BET surface area measurement.

Keywords. Ceramics; synroc; perovskites; electronic materials; microwave synthesis; CaTiO_3 .

1. Introduction

Calcium titanate, CaTiO_3 , with perovskite structure is one of the major phases in Synroc (synthetic rock), a titanate ceramic used for immobilization of high-level nuclear waste (Ringwood *et al* 1979, 1988). It is the major host matrix for strontium, an important radwaste element and can also incorporate significant amounts of lanthanides and actinides (Hanajiri *et al* 1997, 1998). In addition to these nuclear applications, it also finds applications in several electronic devices operating at microwave frequency by virtue of its excellent dielectric properties (Kim *et al* 1999; Suvorov *et al* 2000, 2001; Huang *et al* 2001).

Various methods have been reported in the literature for the synthesis of CaTiO_3 . These include (i) conventional ceramic technique (Kay and Bailey 1957; Redfern 1996), (ii) organometallic (Yang *et al* 1985), (iii) liquid mix method (Balchandran *et al* 1982; Pan *et al* 2003), (iv) chemical co-precipitation method (Gopalakrishnamurthy *et al* 1975), (v) combustion method (Muthuraman and Patil 1994) and (vi) organic–inorganic solution technique (Lee *et al* 2004). Among these methods, the conventional ceramic technique requires high temperatures ($>1200^\circ\text{C}$) and prolonged heating of the reaction components to get the product (Kay and Bailey 1957; Redfern 1996). In other methods, the reaction components are generated *in situ* and are more reactive. Moreover, the particle-to-particle contact in these cases is also more intimate, facilitating the reaction at much lower temperatures. Several other

methods involving the mechanical activation of the reactants have also been proposed to reduce the temperature of the reaction (Mi *et al* 1998, 1999; Evans *et al* 2003; Vukotic *et al* 2004).

In the present paper, we have attempted to synthesize CaTiO_3 from calcium titanyl oxalate (CTO) by heating it in a microwave heating system as well as in a silicon carbide furnace. The product obtained was characterized by X-ray diffraction (XRD), SEM and BET surface area measurement.

2. Experimental

2.1 Synthesis of calcium titanyl oxalate (CTO)

CTO used in the present study was synthesized by chemical co-precipitation method. All the chemicals used were of AnalaR grade. In this method, CaCO_3 was dissolved in equimolar aqueous solution of TiOCl_2 with constant stirring. This mixture was added to aqueous solution of oxalic acid to maintain the mole ratio Ca : Ti : oxalic acid as 1 : 1 : 2. The aqueous solution was kept over sodium hydroxide pellet in a desiccator for 4 to 5 days when a white precipitate was obtained. The precipitate was filtered through Buckner funnel, washed thoroughly first with distilled water and then with acetone and dried in air. Based on chemical analysis, the product could be assigned the molecular formula, $\text{CaTiO}(\text{C}_2\text{O}_4)_2 \cdot 6\text{H}_2\text{O}$. The X-ray diffraction pattern recorded for the product showed that it was amorphous and also no lines of calcium oxalate and titanyl oxalate were visible.

*Author for correspondence (srdharwadkar@hotmail.com)

Figure 1. Simultaneous a. TG, b. DTG and c. DTA of calcium titanyl oxalate (CTO) in flowing nitrogen.

2.2 Thermogravimetry (TG), derivative thermogravimetry (DTG) and differential thermal analysis (DTA) of CTO

The simultaneous TG–DTG–DTA curves of CTO were recorded on 2.380 mg of sample in nitrogen at a heating rate of $10^{\circ}\text{C min}^{-1}$ using the DIAMOND TG-DTA (Perkin Elmer, Germany) Instrument.

2.3 Preparation of calcium titanate (CaTiO_3)

Calcium titanate was prepared by heating CTO in a microwave heating system as well as in a silicon carbide furnace. CTO was heated in a microwave heating system at temperatures of 500°C and 700°C for 1 h. Also CTO was heated in a silicon carbide furnace at 500°C and 700°C for the same period. The product obtained after heat treatment at different temperatures was analysed by X-ray diffraction using X-PERT X-ray diffractometer, Phillips, at a scanning rate of $1^{\circ}2\theta \text{ min}^{-1}$, using monochromatic X-ray beam of wavelength, 0.15405 nm.

3. Results and discussion

3.1 Thermogravimetry (TG), derivative thermogravimetry (DTG) and differential thermal analysis (DTA) of CTO

The TG, DTG and DTA curves of CTO recorded in nitrogen at a heating rate of 10°C/min are shown in figures 1a, b and c, respectively. These data indicate that CTO decomposes in five steps involving dehydration, decarboxylation to intermediate carbonate and decomposition carbonates to give

CaTiO_3 as the final product above 650°C . The endothermic peak in DTA curve located around 105°C could be attributed to dehydration of six water molecules to form anhydrous CTO represented by (1). An endothermic peak in the temperature range $300\text{--}400^{\circ}\text{C}$ is followed by two weak exothermic peaks observed in the range $400\text{--}600^{\circ}\text{C}$, which could have resulted due to decomposition of carboxylate and simultaneous oxidation of evolved CO [(2), (3) and (4)]. Finally, an endotherm is observed at 650°C indicating the formation of CaTiO_3 phase according to (5). TG, DTG and DTA indicate that the thermal decomposition of CTO to form CaTiO_3 in nitrogen atmosphere involves the following sequence of steps.

The five steps involved in the decomposition scheme presented here are based on the stoichiometry of the reaction steps deduced from the mass changes observed in TG. However, the proposed decomposition scheme needs independent support from other complementary techniques like evolved gas analysis. Simultaneous TG–MS studies are in progress to resolve this issue. From the TG and DTA curves it was concluded that the formation of CaTiO_3 from CTO precursor was complete above 650°C . It is interesting to note that in the second and third steps of

Figure 2. XRD pattern of CTO heated in microwave heating system at a. 500°C and b. 700°C for 1 h.

Figure 3. XRD pattern of CTO heated in silicon carbide furnace at a. 500°C and b. 700°C for 1 h.

decomposition of CTO, carbon monoxide is evolved as the gaseous product, which could provide reducing atmosphere in the vicinity of the sample, thereby reducing Ti^{4+} partially to Ti^{3+} which interacts strongly with microwave (Agrawal 1998; Malghe *et al* 2004).

3.2 X-ray diffraction patterns

The X-ray diffraction patterns of CTO calcined in microwave heating system at temperatures 500°C and 700°C, for

1 h are shown in figures 2a and b. The corresponding patterns of the product obtained by heating CTO in silicon carbide furnace at 500°C and 700°C for the same duration are shown in figures 3a and b. The CTO calcined in microwave heating system at a temperature as low as 500°C for 1 h (figure 2a) showed the formation of pure perovskite, CaTiO_3 . The product obtained by heating the same precursor at 700°C in microwave heating system for 1 h was found to be much more crystalline compared to that obtained at 500°C. However, calcination of CTO in silicon

carbide furnace at 500°C for 1 h could not form the product, CaTiO_3 , as shown in figure 3a. This is also corrobo-

Figure 4. SEM photographs of CaTiO_3 : a. MW, 500°C 1 h, b. MW, 700°C 1 h and c. silicon carbide furnace, 700°C 1 h.

rated from the TG curve (figure 1a), which indicates that the reaction involving the formation of CaTiO_3 is not completed at this temperature. The calcination of CTO in silicon carbide furnace at 700°C for 1 h was found to yield CaTiO_3 which was as crystalline as the product obtained by microwave heating at 500°C for the same duration (figure 3b). The results indicate that the temperature of synthesis of CaTiO_3 is lowered considerably by employing microwave heating.

The results presented in the foregoing sections indicate that perovskite, CaTiO_3 , could be synthesized by heating CTO at a temperature as low as 500°C. The reducing atmosphere provided by the evolved carbon monoxide [(2) and (3)] could perhaps be responsible to yield non-stoichiometric TiO_2 , which subsequently reacted at low temperatures to form CaTiO_3 .

Our present observations indicate that the lowering of reaction temperature in microwave heating could be the result of two independent factors, which include the interaction of microwave with defects, involving the role of oxygen vacancies and a number of unpaired electrons present in reactants. In the decomposition of CTO, carbon monoxide is evolved as the gaseous product, which could provide reducing atmosphere in the vicinity of the sample, to yield hypostoichiometric TiO_2 that interacts strongly with microwave, facilitating the solid-state reaction at a much lower temperature. Further, the unpaired electrons in reduced Ti ion i.e. in Ti^{3+} , could facilitate stronger interaction with the magnetic component of the microwave thereby augmenting the reaction rate and lowering the reaction temperature (Dharwadkar 2006).

The SEM photographs of CaTiO_3 prepared by heating CTO at 500°C and 700°C for 1 h using microwave heating system are shown in figures 4a and b. A similar photograph for CaTiO_3 prepared by heating CTO in a silicon carbide furnace at 700°C for 1 h is shown in figure 4c. These photographs indicate that CaTiO_3 prepared at 500°C in microwave heating system yields material of very fine particle size. It can be concluded from these figures that an average particle size of the product obtained by microwave heating increased on increasing the temperature from 500–700°C. The product obtained by heating the precursor to 700°C in air, however, had much finer particle size (figure 3c) compared to that obtained at the same temperature by microwave heating (figure 3b), indicating that the fine particle product obtained at low temperature (500°C) by microwave heating sintered much more rapidly with increasing temperature. This is supported by the surface area measurements made by BET

Table 1. Surface area of CaTiO_3 prepared by different methods.

Method of heating	Temperature (°C)	Surface area (m^2/g)
Microwave heating	500	11.78
	700	5.56
Silicon carbide furnace	700	8.65

gas adsorption technique. The values of surface area listed in table 1, indicate that the surface area of the product obtained by heating the precursor to 700°C in air is higher than that obtained at the same temperature for the same time duration in the microwave heating.

4. Conclusions

Synthesis of CaTiO_3 reported by earlier investigators (Kay and Bailey 1957; Redfern 1996) required high temperature ($>1200^\circ\text{C}$) and long heating periods (more than 12 h). Muthuraman and Patil (1994) synthesized CaTiO_3 at 500°C by combustion method but the product obtained was amorphous and further heat treatment at about 900°C was required for crystallization. We adopted a new method in which crystalline CaTiO_3 was synthesized from CTO heated in microwave heating system at 500°C within an hour. These observations indicate that the microwave heating facilitates the formation of CaTiO_3 from CTO precursor at much lower temperatures.

Acknowledgements

Authors are thankful to the Materials Science Section, Tata Institute of Fundamental Research (TIFR), Mumbai, for recording the SEM photographs of the samples.

References

- Agrawal D K 1998 *Curr. Opin. Solid State and Mater. Sci.* **3** 480
 Balchandran V, Odekirk B and Eror N G 1982 *J. Mater. Sci.* **17** 1656
 Dharwadkar S R 2006 *Indo-US workshop on microwave technology for medical processing—A promising option for tomorrow, Mumbai, ASTM-International, Indian Chapter*, p. 53
 Evans I R, Howard J A K, Screkovic T and Ristic M M 2003 *Mater. Res. Bull.* **38** 1203
 Gopalakrishnamurthy H S, Subba Rao M and Narayan Kutty T R 1975 *Thermochim. Acta* **13** 183
 Hanajiri Y, Yoka H, Mutsui T, Arita Y, Nagasaki T and Shigematsu H 1997 *J. Nucl. Mater.* **247** 285
 Hanajiri Y, Yoka H, Mutsui T, Arita Y, Nagasaki T and Shigematsu H 1998 *Solid State Ionics* **108** 345
 Huang C L, Chen H L and Wu C C 2001 *Mater. Res. Bull.* **36** 1645
 Kay H F and Bailey P C 1957 *Acta Crystallogr.* **10** 219
 Kim W S, Cheon C I, Kang H J, Lee C H, Kim K Y, Nam N and Byun J 1999 *Jpn J. Appl. Phys.* **38** 5633
 Lee S J, Kim Y C and Hwang J H 2004 *J. Ceram. Proc. Res.* **5** 223
 Malghe Y S, Gurjar A V and Dharwadkar S R 2004 *Bull. Mater. Sci.* **27** 217
 Mi G, Saito F, Suzuki S and Waseda Y 1998 *Powder Technol.* **97** 178
 Mi G, Murakimi Y, Saito F, Shindo D and Suzuki S 1999 *Powder Technol.* **105** 162
 Muthuraman M and Patil K C 1994 *Mater. Res. Bull.* **17** 977
 Pan Y, Su Q, Xu H, Chen T, Ge W, Yang C and Wu M 2003 *J. Solid State Chem.* **174** 69
 Redfern S A T 1996 *J. Phys. Condens. Matter* **8** 8267
 Ringwood A E, Kesson S E, Ware N G, Hibberson W and Major A 1979 *Nature* **278** 219
 Ringwood A E, Kesson S E, Reeve K D, Levins D M and Rann E J 1988 in *Radioactive waste forms for future* (eds) W Luttrell and R C Ewing (Amsterdam: Elsevier) p. 233
 Suvorov D, Drazic G, Valant M and Janear B 2000 *Korean J. Cryst.* **11** 195
 Suvorov D, Valant M, Jancar B and Skapin S D 2001 *Acta Chim. Slov.* **48** 87
 Vukotic V M, Screkovic T, Marinkovic Z V, Brankovic G, Cilense M and Arandjelovic D 2004 *Mater. Sci. Forum* **453–454** 429
 Yang Z Z, Yamada H and Miller G R 1985 *J. Solid State Chem.* **41** 185