Templated synthesis and characterization of red-emitting $\text{Ca}_{1-x}\text{Sr}_{1-x}\text{Eu}_{2x}^{3+}\text{SiO}_4$ phosphor for LED applications

ABINAYA MAYAVAN¹, JAYSIVA GANESAMURTHI¹ and SAKTHIVEL GANDHI^{1,2,*}

¹Department of Chemistry, SASTRA Deemed to be University, Thanjavur 613401, India

²Centre for Nanotechnology and Advanced Biomaterials, SASTRA Deemed to be University, Thanjavur 613401, India

*Author for correspondence (sakthivel@scbt.sastra.edu)

MS received 20 March 2018; accepted 1 May 2018; published online 1 September 2018

Abstract. A novel attempt towards the synthesis of red-emitting europium (Eu^{3+})-doped CaSrSiO_4 phosphors has been made through a templated strategy using non-ionic surfactant as template. The concentrations of Eu^{3+} in the host were altered and the optimized concentration to extract the maximum efficacy was analysed. The crystalline structure and morphologies of the synthesized phosphor were studied and analysed. The results show the aggregated rod-like morphology with a continuous porous network that shows the maximum intensity at 10 mol% of dopant.

Keywords. Luminescent materials; templated synthesis; optical properties; white light emission; LED application.

1. Introduction

Phosphors have played a vital role in luminosity of white light-emitting diode (LED). The conventional methods to get white light are RGB method and phosphor method. The RGB method involves using separate chips for generating red, green and blue light; hence this method is complicated and expensive in constructing devices [1]. The phosphor method uses a process to get white photons by integrating InGaN LED chip with yellow-emitting $\text{Y}_3\text{Al}_5\text{O}_{12}:\text{Ce}^{3+}$ (YAG: Ce^{3+}) phosphor. By this method, cool white light is produced by measly red emission components in a yellow phosphor [2–4]. Overcoming these issues, warm white light can be produced using a single emitting centre with yellow phosphor possessing high colour rendering index and low correlated colour temperature.

Because of marvellous luminescence properties, rare earth elements have played a significant role in modern lighting. High colour purity can be achieved by f–f electronic transition of rare earth ions [6–8]. As an important member of the rare earth ions, trivalent europium ion (Eu^{3+}) is an excellent red-emitting activating agent as a result of $^5\text{D}_0$ – $^7\text{F}_J$ ($J = 0, 1, 2, 3, 4$) [9]. Eu^{3+} -doped red-emitting oxide phosphors are easy to prepare, nature friendly and show strong absorption in the region of 400–300 nm; powerful energy transfer takes place from the host matrix to Eu^{3+} [10,11]. Sulphide, nitride and aluminate host matrix silicate are easy to prepare, inexpensive and nature friendly [12–14]. Works have been reported on $\text{CaSrSiO}_4:\text{Eu}^{2+}$, $\text{CaSiO}_3:\text{Eu}^{3+}$ and $\text{Ca}_3\text{Si}_2\text{O}_7:\text{Eu}^{2+}$.

In this article, we report a novel endeavour towards the development of Eu^{3+} -doped CaSrSiO_4 using silica nanoparticles. CaSrSiO_4 phosphor, with a single Eu^{3+} emitting centre

that achieves CCT <4000 K and CRI >80, was obtained at a temperature of 1000°C by a hydrothermal method. The newly synthesized Eu^{3+} -doped CaSrSiO_4 phosphors exhibit a good thermal luminescence stability and high quantum efficiency.

2. Materials and methods

2.1 Materials

Poly(ethylene oxide)–poly(propylene oxide)–poly(ethylene oxide) tri-block copolymer (P-123) and europium chloride hexahydrate ($\text{EuCl}_3 \cdot 6\text{H}_2\text{O}$) were purchased from Sigma-Aldrich. Strontium chloride hexahydrate ($\text{SrCl}_2 \cdot 6\text{H}_2\text{O}$), calcium chloride dihydrate ($\text{CaCl}_2 \cdot 2\text{H}_2\text{O}$), tetraethyl ortho silane (TEOS), hydrochloric acid (HCl) and solvents were purchased from Avra. The afore-mentioned chemicals were used without any further purification.

2.2 Methods

2.2a Synthesis of $\text{Ca}_{1-x}\text{Sr}_{1-x}\text{Eu}_{2x}^{3+}\text{SiO}_4$ phosphor: In order to synthesize $\text{Ca}_{1-x}\text{Sr}_{1-x}\text{Eu}_{2x}^{3+}\text{SiO}_4$ phosphor through templated synthetic strategy, initially 1.23 g of P-123 was taken in 10 ml of methanol and 40 ml of 2 N HCl. The organic precursor of silica (TEOS) was added, which was followed by the addition of other cationic precursors such as $\text{SrCl}_2 \cdot 6\text{H}_2\text{O}$, $\text{CaCl}_2 \cdot 2\text{H}_2\text{O}$ and $\text{EuCl}_3 \cdot 6\text{H}_2\text{O}$. The solution was stirred at room temperature till a homogeneous solution was obtained and it was kept for ageing process at 80°C for 6 h in a Teflon flask. The precipitate was then dried at 100°C overnight and sintered at 1000°C for 4 h in order to

remove the template as well as to get the final phosphor. The chemical ratio of $\text{Sr}^{2+} : \text{Ca}^{2+} : \text{TEOS} : \text{Eu}^{3+}$ was maintained as $1 - x : 1 - x : 1 : 2x$ ($2x = 1, 5, 10$ and 15 mol%).

2.2b Characterization techniques: The crystalline structure of synthesized $\text{Ca}_{1-x}\text{Sr}_{1-x}\text{Eu}_{2x}^{3+}\text{SiO}_4$ phosphor was studied using a powder X-ray diffractometer (XRD) between 20° and 80° (2θ) at a scan speed of 0.01° per step and 1 s per step (XRD, D8 focus, Bruker, Germany). The surface and internal morphology of $\text{Ca}_{1-x}\text{Sr}_{1-x}\text{Eu}_{2x}^{3+}\text{SiO}_4$ phosphors were imaged using a field emission scanning electron microscope (FE-SEM, Tescan, MIRA, Czech Republic) and a field emission transmission electron microscope (FE-TEM, JEM 2100F, JEOL, Japan) with an operating voltage of 20 and 200 kV, respectively. The photoluminescence (PL) excitation and emission behaviours of $\text{Ca}_{1-x}\text{Sr}_{1-x}\text{Eu}_{2x}^{3+}\text{SiO}_4$ ($2x = 1, 5, 10$ and 15 mol%) phosphors were thoroughly studied using a PL spectrometer (FP-8500, Jasco, Japan) with a Xe lamp as the excitation source.

3. Results and discussion

3.1 Crystallinity behaviour of $\text{Ca}_{1-x}\text{Sr}_{1-x}\text{Eu}_{2x}^{3+}\text{SiO}_4$ phosphor

The phosphor samples have been synthesized through templated technique using P-123 as a structure-directing agent with different Eu^{3+} concentrations (1 – 15 mol%). Initially the synthesized phosphors were analysed for their crystal structure. Figure 1 shows the powder XRD patterns of undoped CaSrSiO_4 and $\text{Ca}_{0.95}\text{Sr}_{0.95}\text{Eu}_{0.1}^{3+}\text{SiO}_4$ along with the reference pattern of CaSrSiO_4 (JCPDS No. 77-1619). The result shows the perfect match of undoped and 10 -mol%- Eu^{3+} -introduced CaSrSiO_4 with the pure CaSrSiO_4 phase, which confirms that the introduction of 10 mol% of dopant has not collapsed the crystal phase of CaSrSiO_4 . The crystallite sizes of the undoped and doped CaSrSiO_4 were calculated using the Scherrer formula and found to be 18.15 and 19.04 nm, respectively. The ionic radii of cations Ca^{2+} and Sr^{2+} in the host lattice CaSrSiO_4 are 0.099 and 0.118 nm, respectively. Hence, the dopant Eu^{3+} with ionic radius of 0.095 nm can replace the Ca^{2+} , which has a similar ionic radius, or the bigger ion Sr^{2+} rarely. Hence, the XRD pattern proves that there is no change in the crystal phase of host lattice.

3.2 Morphological studies

The morphological studies of $\text{Ca}_{0.95}\text{Sr}_{0.95}\text{Eu}_{0.1}^{3+}\text{SiO}_4$ phosphors synthesized using P-123 as template have been performed using a SEM and a TEM. The surface morphologies are shown in figure 2A and B, whereas the internal morphologies can be seen in figure 2C and D, which are imaged using the SEM and TEM, respectively. The results show the morphology of around $1\text{-}\mu\text{m}$ -sized aggregated rods

Figure 1. Powder XRD patterns of (a) reference (JCPDS No. 77-1619), (b) $\text{Ca}_{0.95}\text{Sr}_{0.95}\text{Eu}_{0.1}^{3+}\text{SiO}_4$ phosphor and (c) undoped CaSrSiO_4 .

with nanoporous structure due to the use of template P-123 during synthesis. Initially, P-123 makes spherical micelles when it reaches the CMC (critical micellar concentration), which get aggregated to one another to form a rod-like structure. The introduced cations (Sr^{2+} , Ca^{2+} and Eu^{3+}) and silica precursor (TEOS) interact on the surface of aggregated rod-structured micelles. The interaction leads to the hydrolysis of all the cations on the surface of micelles, which will be dried and calcined later. The porosity in the phosphor is formed due to the removal of template during the calcination process at high temperature. TEM images also confirm the aggregated rod structure of $\text{Ca}_{0.95}\text{Sr}_{0.95}\text{Eu}_{0.1}^{3+}\text{SiO}_4$, whereas the fine local structures of the same phosphor are verified using a high-resolution (HR) image. It shows the continuous lattice fringes without any defects, which further confirm the high crystallinity nature of $\text{Ca}_{0.95}\text{Sr}_{0.95}\text{Eu}_{0.1}^{3+}\text{SiO}_4$ phosphor. The d spacing of the phosphor was also calculated using the HR image, which was found to be 0.431 nm. Figure 2E shows the selected area electron diffraction pattern (SAED) of $\text{Ca}_{0.95}\text{Sr}_{0.95}\text{Eu}_{0.1}^{3+}\text{SiO}_4$ phosphor, which confirms that the introduction of dopant has not collapsed the crystal structure of the host CaSrSiO_4 .

3.3 PL studies

The PL behaviours of synthesized $\text{Ca}_{1-x}\text{Sr}_{1-x}\text{Eu}_{2x}^{3+}\text{SiO}_4$ ($2x = 1, 5, 10$ and 15 mol%) phosphors have been analysed by PL spectroscopy and presented in figure 3. Initially the excitation was recorded at 615 nm of emission, which corresponds to the $^5\text{D}_0 - ^7\text{F}_2$ transition of Eu^{3+} . There are sharp peaks obtained between 300 and 500 nm along with a broad band at 250 nm wavelength. The broad band in ultraviolet (UV) region peaking at 250 nm is observed due to the well-known charge transfer band (CTB), which arises by

Figure 2. (A, B) SEM and (C, D) TEM images and (E) SAED pattern of $\text{Ca}_{0.95}\text{Sr}_{0.95}\text{Eu}_{0.1}\text{SiO}_4$ phosphor.

Figure 3. PL (A) excitation and (B) emission studies of $\text{Ca}_{1-x}\text{Sr}_{1-x}\text{Eu}_{2x}^{3+}\text{SiO}_4$ ($2x = 1, 10, 5$ and 15 mol%). (C) CIE colour coordinate of $\text{Ca}_{0.95}\text{Sr}_{0.95}\text{Eu}_{0.1}^{3+}\text{SiO}_4$.

electron transfer from oxygen $2p$ state to $4f$ state of Eu^{3+} ($\text{O}^{2-}-\text{Eu}^{3+}$). There are several other sharp peaks registered at various wavelengths such as 360, 388, 395, 419 and 460 nm, which can be well correlated to the $4f-4f$ transitions of Eu^{3+} (${}^7\text{F}_0-{}^5\text{D}_4$), (${}^7\text{F}_0-{}^5\text{L}_7$), (${}^7\text{F}_0-{}^5\text{L}_6$), (${}^7\text{F}_0-{}^5\text{D}_3$) and (${}^7\text{F}_0-{}^5\text{D}_2$), respectively. The maximum intensity is recorded for the transition from ${}^7\text{F}_0$ to ${}^5\text{L}_6$ at 395 nm, while the intensities of other peaks are distributed in the order of (${}^7\text{F}_0-{}^5\text{D}_2$) at 460 nm > (${}^7\text{F}_0-{}^5\text{L}_7$) at 388 nm > (${}^7\text{F}_0-{}^5\text{D}_4$) at 360 nm > (${}^7\text{F}_0-{}^5\text{D}_3$) at 419 nm. As the maximum intensity is recorded at 395 nm due to ${}^7\text{F}_0-{}^5\text{L}_6$ transition, it has been set as the excitation wavelength to analyse the emission behaviours of phosphors.

The emission spectra of synthesized $\text{Ca}_{1-x}\text{Sr}_{1-x}\text{Eu}_{2x}^{3+}\text{SiO}_4$ ($2x = 1, 5, 10$ and 15 mol%) phosphors recorded at 395 nm of excitation wavelength are shown in figure 3B. It confirms the Eu^{3+} characteristic emission by showing the sharp peaks at 582, 590, 615 and 630 nm, which correspond to the ${}^5\text{D}_0-{}^7\text{F}_x$ ($x = 0, 1, 2$ and 3) transitions, respectively. The peak at 615 nm due to transition ${}^5\text{D}_0-{}^7\text{F}_2$ is recorded as the maximum intensity peak, whereas the other peaks at 582 nm (${}^5\text{D}_0-{}^7\text{F}_0$), 590 nm (${}^5\text{D}_0-{}^7\text{F}_1$) and 630 nm (${}^5\text{D}_0-{}^7\text{F}_3$) show less and similar intensities. The concentration of dopant (Eu^{3+}) in the host lattice CaSrSiO_4 has been changed (1, 5, 10 and 15 mol%) in order to analyse the optimized concentration to achieve the maximum emission efficiency. The excitation and emission spectra of the phosphor with different dopant concentrations are studied and shown in figure 3. It shows the increase in intensity when the concentration of dopant increases from 1 to 10 mol%. However, there is a decrease in intensity recorded when the dopant concentration is increased further from 10 to 15 mol%. The decrease in the intensity is due to the concentration quenching. It happens when two dopants in a single host come closer. Hence, the optimized concentration of Eu^{3+} in CaSrSiO_4 host synthesized using P-123 as template is found to be 10 mol%. The Commission International De I-Eclairage (CIE) 1931 chromaticity colour coordinate for the phosphor with 10 mol% of Eu^{3+} was calculated to be (0.63, 0.36) (figure 3C).

4. Conclusion

In summary, the current work showed the first-time synthesis of $\text{Ca}_{1-x}\text{Sr}_{1-x}\text{Eu}_{2x}^{3+}\text{SiO}_4$ ($2x = 1, 5, 10$ and 15 mol%) phosphors through templated technique using non-ionic tri-block copolymer P-123 as surfactant. The results show the porous aggregated rod-like morphology with high crystalline nature without any defects, which can also be well correlated with XRD pattern. PL studies confirm the efficient red emissive behaviour of $\text{Ca}_{1-x}\text{Sr}_{1-x}\text{Eu}_{2x}^{3+}\text{SiO}_4$ phosphors with the optimum dopant concentration of 10 mol%. Hence, this phosphor can be further utilized as a red-emitting material, which can be fixed along with a green phosphor on a near-UV LED to achieve warm white light with low CCT and high CRI.

Acknowledgements

We are grateful to the SERB, Department of Science and Technology (EMR-2016-005574), for the financial support. We also thank SASTRA Deemed to be University, Thanjavur, for the infrastructural support.

References

- [1] Piquette A, Bergbauer W, Galler B and Mishra K C 2016 *ECS J. Solid State Sci. Technol.* **5** 3146
- [2] Setlur A 2009 *Electrochem. Soc. Interface* **16** 32
- [3] Karmes M R, Shchekin O B, Mueller G O and Zhou L 2007 *J. Disp. Technol.* **3** 160
- [4] Nakamura S 1997 *Proc. SPIE* **3002** 26
- [5] Yan X H, Zheng S S, Yu R M, Jing C, Xu Z W, Liu C J *et al* 2008 *Trans. Nonferrous Met. Soc. China* **18** 648
- [6] Lian S X, Lin J H and Su M Z 2001 *J. China Rare Earth Soc.* **19** 602
- [7] Justel T, Nikol H and Ronda C 1998 *Angew. Chem. Int. Ed.* **37** 3084
- [8] Liu X, Yan L and Lin J 2009 *J. Electrochem. Soc.* **156** 1
- [9] Zhu G, Ci Z, Shi Y, Que M, Wang Q and Wang Y 2013 *J. Mater. Chem. C* **1** 5960
- [10] Park S H, Lee K H, Unithrattil S, Yoon H S, Jang H G and Im W B 2012 *J. Phys. Chem. C* **116** 26850
- [11] Zhang N, Guo C and Jing H 2013 *RSC Adv.* **3** 7495
- [12] Meyer J and Tappe F 2015 *Adv. Opt. Matter.* **3** 424
- [13] Dai P, Li C, Zhang X T, Xu J, Chen X, Wang X L *et al* 2016 *Light: Sci. Appl.* **5** 16024
- [14] Terraschke H and Wickleder C 2015 *Chem. Rev.* **115** 11352