

## Studies on the valence electronic structure of Fe and Ni in $\text{Fe}_x\text{Ni}_{1-x}$ alloys

D K BASA<sup>1,\*</sup>, S RAJ<sup>2</sup>, H C PADHI<sup>2</sup>, M POLASIK<sup>3</sup> and F PAWLOWSKI<sup>3</sup>

<sup>1</sup>Department of Physics, Utkal University, Bhubaneswar 751 004, India

<sup>2</sup>Institute of Physics, Bhubaneswar 751 005, India

<sup>3</sup>Faculty of Chemistry, Nicholas Copernicus University, 87-100 Toruń, Poland

\*Email: basa@hpc27.ac.iopb.res.in

**Abstract.**  $K_\beta$ -to- $K_\alpha$  X-ray intensity ratios of Fe and Ni in pure metals and in  $\text{Fe}_x\text{Ni}_{1-x}$  alloys ( $x = 0.20, 0.50, 0.58$ ) exhibiting similar crystalline structure have been measured following excitation by 59.54 keV  $\gamma$ -rays from a  $^{241}\text{Am}$  point source, to understand as to why the properties of permalloy  $\text{Fe}_{0.2}\text{Ni}_{0.8}$  is distinct from other alloy compositions. It is observed that the valence electronic structure of  $\text{Fe}_{0.2}\text{Ni}_{0.8}$  alloy is totally different from other alloys which may be attributed to its special magnetic properties.

**Keywords.**  $K_\beta$ -to- $K_\alpha$  ratio; alloy; valence electronic structure.

**PACS Nos** 32.30.Rj; 32.70.Fw

### 1. Introduction

$\text{Fe}_x\text{Ni}_{1-x}$  alloys have emerged as technologically important materials due to the rapid advance of magnetoelectronics [1]. Although the studied  $\text{Fe}_x\text{Ni}_{1-x}$  alloys ( $x = 0.2, 0.5$  and  $0.58$ ) crystallize in the same  $\gamma$  (fcc) phase, permalloy, a member of the family of  $\text{Fe}_x\text{Ni}_{1-x}$  alloys (with  $x = 0.2$ ), exhibits distinct physical properties of vanishingly small magnetostriction, low coercivity and high permeability, which makes it the material of choice for magnetic recording media, sensors and non-volatile magnetic random access memory. Accordingly, it is very important to have a detailed knowledge of the valence electronic structure of Fe and Ni in various  $\text{Fe}_x\text{Ni}_{1-x}$  alloys. Since  $K_\beta$ -to- $K_\alpha$  X-ray intensity ratio has been reported [2–7] to be a sensitive physical parameter to investigate the changes in the valence electronic structure of 3d-transition metals [2], we have undertaken the study of the valence electronic structure of Fe and Ni in the  $\text{Fe}_x\text{Ni}_{1-x}$  alloys for various compositions ( $x = 0.2, 0.5$  and  $0.58$ ) exhibiting similar crystalline structure to understand as to why the physical properties of  $\text{Fe}_{0.2}\text{Ni}_{0.8}$  alloy are drastically different from other alloy compositions. The important results of the study are reported here while the details have been communicated elsewhere [7].

## 2. Experiment

The measurements were carried out using high purity alloys (in powder form) procured from Alpha, a Johanson Mathey Company, UK. The powder material is pelletized and 59.54 keV  $\gamma$ -rays from a 200 mCi  $^{241}\text{Am}$  point-source were made to incident on the pellet to ionize the target atoms. The emitted X-rays were detected and were finally recorded in a Canberra PC based Model S-100 multichannel analyzer. The X-ray spectra thus obtained were carefully analyzed with the help of a multi-Gaussian least-square fitting programme [8] using a non-linear background subtraction. Details regarding the experimental arrangement as well as data analysis have been reported elsewhere [3,4,7].

## 3. Results and discussion

The experimental results for the  $K_{\beta}$ -to- $K_{\alpha}$  X-ray intensity ratios of Fe and Ni in pure metals and in the  $\text{Fe}_x\text{Ni}_{1-x}$  alloys ( $x = 0.2, 0.5$  and  $0.58$ ) before and after various corrections are presented in table 1. The errors quoted in the table are only statistical. The  $3d$  electron populations of Fe and Ni for various samples are presented in table 2. These have been

**Table 1.** Experimental  $K_{\beta}/K_{\alpha}$  X-ray intensity ratios for Fe and Ni in  $\text{Fe}_x\text{Ni}_{1-x}$  alloys.

Composition ( $x$ )	$K_{\beta}$ -to- $K_{\alpha}$ ratio of Fe		$K_{\beta}$ -to- $K_{\alpha}$ ratio of Ni	
	Before correction	After correction	Before correction	After correction
0	—	—	$0.1808 \pm 0.0016$	$0.1346 \pm 0.0012$
0.2	$0.1737 \pm 0.0010$	$0.1326 \pm 0.0008$	$0.1723 \pm 0.0010$	$0.1314 \pm 0.0008$
0.5	$0.1743 \pm 0.0009$	$0.1321 \pm 0.0007$	$0.1808 \pm 0.0010$	$0.1371 \pm 0.0008$
0.58	$0.1726 \pm 0.0008$	$0.1309 \pm 0.0006$	$0.1822 \pm 0.0010$	$0.1386 \pm 0.0008$
1.0	$0.1764 \pm 0.0009$	$0.1307 \pm 0.0007$	—	—

**Table 2.** Evaluated  $3d$ -electron population values and total number of ( $4s, 4p$ ) electrons for Fe and Ni in various samples.

Kind of sample	Evaluated	Total	Evaluated	Total
	$3d$ -electron population for Fe	number of ( $4s, 4p$ ) electrons for Fe	$3d$ -electron population for Ni	number of ( $4s, 4p$ ) electrons for Ni
Pure Fe	$7.39 \pm 0.29$	$0.61 \pm 0.29$	—	—
Pure Ni	—	—	$8.54 \pm 0.39$	$1.46 \pm 0.39$
$\text{Fe}_{0.2}\text{Ni}_{0.8}$	$6.69 \pm 0.26$	$1.31 \pm 0.26$	$9.93 \pm 0.52$	$0.07 \pm 0.52$
$\text{Fe}_{0.5}\text{Ni}_{0.5}$	$6.86 \pm 0.24$	$1.14 \pm 0.24$	$7.81 \pm 0.21$	$2.19 \pm 0.21$
$\text{Fe}_{0.58}\text{Ni}_{0.42}$	$7.31 \pm 0.24$	$0.69 \pm 0.24$	$7.44 \pm 0.19$	$2.56 \pm 0.19$

**Table 3.** Comparison of estimated weighted average number of  $3d$  and  $(4s, 4p)$  electrons for various  $\text{Fe}_x\text{Ni}_{1-x}$  alloys with the superposition values of  $3d$  and  $(4s, 4p)$  electrons obtained from the pure metal values.

Kind of sample	Weighted average number of $3d$ electrons	Superposition of $3d$ electrons obtained from pure metal values	Weighted average number of $(4s, 4p)$ electrons	Superposition of $(4s, 4p)$ electrons from pure metal values
$\text{Fe}_{0.2}\text{Ni}_{0.8}$	$9.28 \pm 0.42$	$8.31 \pm 0.32$	$0.32 \pm 0.42$	$1.29 \pm 0.32$
$\text{Fe}_{0.5}\text{Ni}_{0.5}$	$7.34 \pm 0.16$	$7.97 \pm 0.24$	$1.66 \pm 0.16$	$1.03 \pm 0.24$
$\text{Fe}_{0.58}\text{Ni}_{0.42}$	$7.36 \pm 0.16$	$7.87 \pm 0.24$	$1.48 \pm 0.16$	$0.97 \pm 0.24$

evaluated by comparing the experimental values of  $K_\beta$ -to- $K_\alpha$  intensity ratio with the results of MCDF calculations performed for various valence electronic configurations [2] of Fe and Ni. The  $3d$  electron populations, thus obtained, for pure Fe and Ni metals (table 2) are found to be in close agreement with the results of band structure calculations of Papaconstantopoulos [9] (6.93 for Fe and 8.97 for Ni) and Hodges *et al* [10] (8.82 for Ni). In order to answer as to why the physical properties of  $\text{Fe}_{0.2}\text{Ni}_{0.8}$  alloy are distinct as compared to the other two alloys, we have calculated the *weighted average* numbers of  $3d$  and  $(4s, 4p)$  electrons per one atom as well as the superposition of  $3d$  and  $(4s, 4p)$  electrons, as obtained from pure metal values, for all the studied  $\text{Fe}_x\text{Ni}_{1-x}$  alloys and the results are shown in table 3. It can be seen from table 3 that in the case of  $x=0.5$  and  $0.58$  the weighted average numbers of  $3d$  electrons in the  $\text{Fe}_x\text{Ni}_{1-x}$  alloys (the second column of table 3) are smaller than the superpositions of the number of  $3d$  electrons of pure Fe and Ni metals (the third column of table 3). In the case of  $\text{Fe}_{0.2}\text{Ni}_{0.8}$  alloy the weighted average number of  $3d$  electrons is very large ( $9.28 \pm 0.42$ ) and differs considerably from the superposition of the number of  $3d$  electrons of pure Fe and Ni metals ( $8.31 \pm 0.32$ ). However, in the case of  $(4s, 4p)$  electrons the situation is opposite. Clearly, there is considerable difference of the valence electronic structure of  $\text{Fe}_{0.2}\text{Ni}_{0.8}$  alloy with respect to the other two alloys.

#### 4. Conclusion

The study of  $K_\beta$ -to- $K_\alpha$  intensity ratio along with the MCDF calculation reveals a large weighted average number of  $3d$  electrons ( $9.28 \pm 0.42$ ) and negligible weighted average number of  $(4s, 4p)$  electrons ( $0.32 \pm 0.42$ ) for  $\text{Fe}_{0.2}\text{Ni}_{0.8}$  alloy as compared to other studied alloys. The considerable difference in the valence electronic structure of  $\text{Fe}_{0.2}\text{Ni}_{0.8}$  alloy may possibly be the reason for the high permeability and other alluring magnetic properties of this alloy.

#### References

- [1] G A Prinz, *Phys. Today* **48**, 55 (1995); *Science* **282**, 1660 (1998)
- [2] M Polasik, *Phys. Rev.* **A58**, 1840 (1998)
- [3] C R Bhuinya and H C Padhi, *J. Phys. B: At. Mol. Opt. Phys.* **25**, 5283 (1992)
- [4] B B Dhal, T Nandi and H C Padhi, *Nucl. Instrum. Methods* **B101**, 327 (1995)

- [5] S Raj, H C Padhi, M Polasik and D K Basa, *Solid State Commun.* **110**, 275 (1999)
- [6] S Raj, H C Padhi, D K Basa, M Polasik and F Pawłowski, *Nucl. Instrum. Methods* **B152**, 417 (1999)
- [7] S Raj, H C Padhi, M Polasik, F Pawłowski and D K Basa, *Phys. Rev.* **B63**, 73109 (2001)
- [8] Computer code NSCSORT (unpublished)
- [9] D A Papaconstantopoulos, *Handbook of band structure of elemental solids* (Plenum Press, New York, 1986)
- [10] L Hodges, H Eherenreich, N D Lang, *Phys. Rev.* **152**, 505 (1966)